

## TECHNICAL INFORMATION

# GS 70/H-AM-AS



**Description:** Lead free flexible PVC compound, **phthalates FREE**



**Application:** injection moulding technical item , Fungus and Bacterial Resistant, Antistatic

**Standard :** -----

### Technical characteristics:

Property	Test method	Unit	Tolerance	Value
Density(natural colour)	ISO 1183	gr/cm <sup>3</sup>	± 0,02	1,21
Hardness Shore "A" 15"	ISO 868	point	± 2	70
Tensile strength	ISO 527	N/mm <sup>2</sup>	≥	14.5
Elongation at break	ISO 527	%	≥	350

The typical values reported in the table have been obtained from measurements made on extruded samples or pressed plates

**Storage:** compound must be stored at ambient temperature (not exceeding 30 °C) in closed and unbroken packaging, in order to avoid exposure to sunlight and water absorption.

**Packaging:** 25Kg plastic bags, big bags, carton oktabins or in silos truck.

For further information please contact [info@fainplast.com](mailto:info@fainplast.com)

Edition 01/2013

**Notes:** the description contained herein are provided to customers as a general information for the purposes the product is intended for. These reflect FAINPLAST knowledge at the time of publication. By the information contained here in FAINPLAST won't release any warranty and/or give any suggestion on the use of the product, or grant any franchise on existing patents. The end-user, transformer shall always check the specific suitability of the product for the purposes it is intended for and its compatibility with process specifications. This document does not form part of any contract with customer.